MODEL No: 1AA (GENERIC) Description: AA SIZE NI-CAD

## Capacities Available: 500,600,700,800,900 and 1000 mAh

## D2 D1 d1d2H1 H2 High Top Low Top (Not Standard) (Standard) Dimension of the cell with tube $| \Phi 14.1 \pm 0.2 | D2$ $\Phi 14.1 \pm 0.2$ $\Phi 4.75 \pm 0.05$ d2 $\Phi$ 8.1 $\pm$ 0.05 H1 $|49.5 \pm 0.5|$ H2 $48.0 \pm 0.5$

## **Specification**

Nominal C	As Spec			
Nominal V	1.2 V			
Charge current		Trickle	0.05 - 0.1 CA	
		Standard	0.1 CA	
		Quick	0.3 CA	
		Fast	0.5 CA	
		Rapid (not 1Ah)	1.0 CA	
Charge time		Standard	14~16 Hrs	
		Quick	4~5 Hrs	
		Fast	2.5Hrs	
		Rapid (not 1Ah)	1.2 Hrs	
	Charge	Standard	0~45°C	
Ambient		Quick	10~45°C	
Temperature		Fast	10~45°C	
	Discharge		-30~60°C	
	Storage		-30~65°C	
Max Hı	85%			
Intern	$Max \leq 21 \text{ m}\Omega$			
(After				
Weight			25g	

## **Performance**

Test	Unit	Specification	Test Conditions	
Capacity	Mah	≥Capacity as specified	Standard Charge and then Discharge (0.2CA for 5 Hours) Allowing up to 3 cycles to achieve full capacity	
Open Circuit Voltage(OCV)	V/cell	≥1.25	Within I hour after standardCharge	
High Rate Discharge(1C)	Minute	≥54	Standard Charge then I hour rest. Before discharge by 1CA )to 1.0V/cell. Allowing up to 3 cycles to achieve full capacity.	
Overcharge	/	No leakage nor explosion	(0.1C) Charge 28 days	
Charge Retention	Mah	≥ 0.7C (70%)	Standard Charge, Storage 28 days, Standard Discharge	
IEC Cycle Life	Cycle	≥700	IEC285(1993)4.4.1	
Leakage		No leakage nor deformation	Fully charged at: (0.3C) for 4.5hrs. Then stand for 14 days	

- Maximum Cell voltage should be considered to be 1.70 Volts.
- $-\Delta V$  termination should be set at 20-30 mV/cell.
- DT/dt termination should be 0.5°C/Minute.

NOTE: 1000mAh is not suitable for Rapid charge.